## BLUE CRAB CAN SEAM EVALUATION RECORD FOR 401x301 Tinplate, Aluminum Ends

				Address: 123 Harvest Way, Seaside, MD 12345 Person Responsible: Packing Room  Frequency: Conduct a complete evaluation at start-up and after adjustment Visual check, every batch.  The Overlap = CH + BH + .012 - L							
Date	Tigh Time	Code	Visual Accept/ Reject	Thickness .060±.002	Length (L) .125 maximum	Body-hook (BH) .080±008	Cover-hook (CH) .080±008	Overlap .045 minimum	Tightness 80-100%	Pressure/ Vacuum Accept/ Reject	Operator' Initials
10/13/03	8:48am	A 25a - 03	Acc.	0.61	.121	.078	.079	.048	100	VAC. / ACC.	RR
				0.60	.122	-079	. 079	.058			
				0.59	,120	. 080	. 080	.052			
			Acc.								
	(1:04 AM	B252-03								2.	RR
			Acc.								1
10/13/03	2:35pm	C 252-03									RR
Comments:								14			
						et .					